

TRANSMITTAL LETTER TO THE UNITED STATES

30394-1068

DESIGNATED/ELECTED OFFICE (DO/EO/US)

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

CONCERNING A FILING UNDER 35 U.S.C. 371

10/089423

INTERNATIONAL APPLICATION NO
PCT/NL00/00699INTERNATIONAL FILING DATE
29 September 2000 (29.09.2000)PRIORITY DATE CLAIMED
30 September 1999 (30.09.1999)

TITLE OF INVENTION

PROCESS FOR THE PREPARATION OF A COATING, A COATED SUBSTRATE, AN ADHESIVE, A FILM OR SHEET, FOR THE THUS OBTAINED PRODUCTS AND THE COATING MIXTURE TO BE USED IN THE PROCESS

APPLICANT(S) FOR DO/EO/US

Laurentius Cornelius Josephus HESSELMANS and Dirk Pieter SPEK

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31)
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☒ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☒ Other items or information:


Unsigned Declaration and Power of Attorney for Patent Application
Associate Power of Attorney

10/089423

JC10 Rec'd PCT/PTO 29 MAR 2002

PATENT APPLICATION

I hereby certify that this paper is being deposited with the United States Postal Service on **March 29, 2002**, in an envelope as "Express Mail Post Office to Addressee" mailing Label No **EV003481995US** addressed to Box PCT, Commissioner for Patents, Washington, D.C. 20231


Annette M. Turk, Legal Assistant

March 29, 2002
(Date)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Laurentius Cornelius Josephus Hesselmans :
and Dirk Pieter Spek :

Serial No.: UNKNOWN :

Examiner: UNKNOWN

Priority claimed to PCT/NL00/00699 :

Filed: Herewith (March 29, 2002) :

Group Art Unit: UNKNOWN

For. PROCESS FOR THE PREPARATION OF A
COATING, A COATED SUBSTRATE, AN ADHESIVE
A FILM OR SHEET, FOR THE THUS OBTAINED
PRODUCTS AND THE COATING MIXTURE TO BE
USED IN THE PROCESS

FIRST PRELIMINARY AMENDMENT

Box: PCT
Commissioner for Patents
Washington, D.C. 20231

Sir,

Please amend the application, without prejudice, as follows (note that the claims were amended in response to the PCT First Written Opinion).

In the Claims:

Delete claim 8 and amend the claims as follows:

1 (Twice Amended) A process for the preparation of a coating, adhesive, film or sheet wherein a mixture of a polyisocyanate functional, a polyepoxide functional, a polyanhydride functional or a polyketone functional compound or polymer and a dispersion of a compound containing reactive hydrogen, which compound is a polyhydrazide, a polysemicarbazide, a polysulphonylhydrazide, or a carbodihydrazide, in a material which contains no groups which are reactive toward the compound containing reactive hydrogen, in which mixture the reactivities of the isocyanate, epoxide, anhydride or the ketone functions towards the hydrazide, semicarbazide, sulphonylhydrazide or carbodihydrazide is absent or low at ambient conditions and the reactivities are high at temperatures of 50 to 300° C, is applied onto a substrate at ambient temperature, followed by reacting the above compounds at 50 to 300° C for 1 to 10 min, or is applied onto a substrate at ambient temperature, followed by immersing the coated substrate into water of 20 to 100° C for 1 to 10 min.

2 (Amended) The process according to claim 1, wherein at ambient temperature said compound containing reactive hydrogen is a solid material, a powder, a granule, a flake or grind or a mixture thereof.

3. (Amended) The process according to claim 2 wherein size of the grind of said compound containing reactive hydrogen is from 0.5 to 200 µm.

4. (Amended) The process according to claim 1, wherein said polyhydrazide is selected from the group consisting of oxalic dihydrazide, malonic dinydrazide, succinic dinydrazide, adipic dihydrazide, sebacic dihydrazide, dodecanoic dihydrazide, isophthalic dihydrazide, piperazine N,N'-dihydrazide, m-benzene-dihydrazide, and p-benzene-dihydrazide.

Ser. No. UNKNOWN

5. (Twice Amended) The process according to claim 4, wherein said polyhydrazide is selected from the group consisting of adipic dihydrazide and carbodihydrazide
6. (Twice Amended) The process according to claim 1, wherein said polysemicarbazide is selected from the group consisting of ethane-disemicarbazide, butane-disemicarbazide, propane-disemicarbazide, hexane-disemicarbazide, para-benzene-disemicarbazide, toluene-2,4-disemicarbazide, toluene-2,4-disemicarbazide, bis (4-semicarbazido-phenyl)ether, bis (4,4'-hydrozide)-3,3'-dimethoxy biphenyl, di-N,N'-methylamino urea, 4,4'-methylene-bis (cyclohexene semicarbazide), 3-semicarbazide-methyl-3,5,5-trimethylcyclohexyl-semicarbazide and mixtures thereof.
7. (Twice Amended) The process according to claim 4, wherein said polysulphonyl hydrazide is selected from the group consisting of p,p'-oxybis benzene sulphonyl hydrazide, bis(methylhydrazido)sulphate, bis (methylhydrazidosulphonyl)piperazine, and bis p-(hydrazidosulphonylamino)benzene.
9. (Twice Amended) The process according to claim 1, wherein the material which contains no groups which are reactive towards the compound containing reactive hydrogen, is a polyether, a polyester, a polycarbonate, a polyacrylate, a polyvinylalkylether, a polyurethane, a polyacrylate, a polyvinylalkylether, or a polyurethane.
10. (Twice Amended) The process according to claim 1, wherein said mixture of the polyisocyanate functional, the polyepoxy functional, or the polyketone functional compound or polymer and the compound containing reactive hydrogen, is solvent free

11. (Twice Amended) The process according to claim 1, wherein said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in an equivalent ratio of 0.5 to 1.5, applied onto a substrate and the so obtained covered or impregnated substrate is heated to a temperature of 50 to 300° C for 1 to 10 min.

12. (Twice Amended) The process according to claim 1, wherein said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in an equivalent ratio of 0.5 to 1.5, and applied onto a substrate whereafter the covered or impregnated substrate is immersed into water of 20 to 100° C for 1 to 10 min.

13. (Twice Amended) Coatings, coated substrates, adhesives, films, sheets, impregnated substrates, synthetic leathers, in mold coatings, coated leathers, coated polyvinylchlorides, coated non-wovens, coated coagulated polyurethane substrates, and breathable coated substrates, obtained by applying the process of claim 1.

14. (Twice Amended) A coating mixture to be applied in the process of claim 1 wherein the coating mixture comprises a mixture of a polyisocyanate functional, a polyepoxyde functional, a polyanhydride functional or a polyketone functional compound and a dispersion of a compound containing reactive hydrogen, which compound is a polydiazide, a polysemicarbazide, a polysulphonylhydrazide, carbodihydrazide, in a material which contains no groups which are reactive towards the compound containing reactive hydrogen, in which mixture the reactivities of the isocyanate, epoxide, anhydride or the ketone functions towards the hydrazide, semicarbazide sulphonylhydrazide or carbodihydrazide is absent or low at ambient conditions and the reactivities are high at temperatures of 50 to 300° C or when the mixture is immersed into water

15. (Twice Amended) A coating mixture according to claim 1, wherein the mixture of the polyisocyanate functional compound, the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature for at least one day.

16. (Twice Amended) A coating mixture according to claim 14, wherein the mixture of the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature as a one pot system.

17. (Twice Amended) A coating mixture according to claim 14, wherein the compound containing reactive hydrogen is present as grind which is dispersed in a material which is non-reactive towards the material containing reactive hydrogen

18. (Twice Amended) A coating mixture according to claim 14, wherein at ambient temperature the compound containing reactive hydrogen is a solid, which is a powder, a granule, a flake or a grind or a mixture thereof.

19 (Twice Amended) A coating mixture according to claim 18, wherein particle size of the grind or of the dispersion of the compound containing reactive hydrogen is from 0.5 to 200 μm .

Ser. No. UNKNOWN

REMARKS

The foregoing amendment to the claims is being offered in a format acceptable to the U.S. Patent and Trademark Office. No new matter is presented by this Amendment. Entry of this amendment by the Examiner is respectfully requested.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached paper is captioned "**Version with Markings to Show Changes Made.**"

Authorization is given to charge payment of any fees required, or credit any overpayment, to Deposit Acct. 13-4213. A duplicate of this paper is enclosed for accounting purposes.

Respectfully submitted,

Dated: March 29, 2002

By:


Jeffrey D. Myers, Reg. No. 35,964
Direct line: (505) 998-1502

PEACOCK, MYERS & ADAMS, P.C.
Attorneys for Applicant(s)
P.O. BOX 26927
Albuquerque, New Mexico 87125-6927

Telephone: (505) 998-1500
Facsimile: (505) 243-2542

[\\JDM\DOCS\AMDS\Los&Stig\Stahl699.PAM doc] 30394-1068

Version with Markings to Show Changes Made

In the Claims.

1. (Twice Amended) [The] A process for the preparation of a coating, adhesive, film or sheet [characterized, in that] wherein a mixture of a polyisocyanate functional, a polyepoxide functional, a polyanhydride functional or a polyketone functional compound or polymer and a dispersion of a compound containing reactive hydrogen, which compound is a polyhydrazide, a polysemicarbazide, a polysulphonylhydrazide, or a carbodihydrazide, in a material which contains no groups which are reactive toward the compound containing reactive hydrogen, in which mixture the reactivities of the isocyanate, epoxide, anhydride or the ketone functions towards the hydrazide, semicarbazide, sulphonylhydrazide or carbodihydrazide is absent or low at ambient conditions and the reactivities are high at temperatures of 50 to 300° C, is applied onto a substrate at ambient temperature, followed by reacting the above compounds at 50 to 300° C for 1 to 10 min, or is applied onto a substrate at ambient temperature, followed by immersing the coated substrate into water of 20 to 100° C for 1 to 10 min

2. (Amended) The process according to claim 1, [characterized, in that] wherein at ambient temperature said compound containing reactive hydrogen is a solid material, a powder, a granule, a flake or grind or a mixture thereof [which is preferably ground].

3. (Amended) The process according to [claims 1 and 2, characterized, in that] claim 2 wherein [the actual] size of the grind of said compound containing reactive hydrogen[,] is from 0.5 to 200 μm [and is preferably from 0.5 to 60 μm and is more preferably from 0,5 to 15 μm]

Ser. No UNKNOWN

4. (Twice Amended) The process according to claim 1, [characterized, in that] wherein said polyhydrazide is selected from the group consisting of oxalic dihydrazide, malonic dinydrazide, succinic dinydrazide, adipic dihydrazide, sebacic dihydrazide, dodecanoic dihydrazide, isophthalic dihydrazide, piperazine N,N'-dihydrazide, m-benzene-dihydrazide, and p-benzene-dihydrazide

5. (Twice Amended) The process according to claim 4, [characterized, in that] wherein said [the] polyhydrazide is selected from the group consisting of adipic dihydrazide [or] and carbodihydrazide

6. (Twice Amended) The process according to claim 1, [characterized, in that] wherein said polysemicarbazide is selected from the group consisting of ethane-disemicarbazide, butane-disemicarbazide, propane-disemicarbazide, hexane-disemicarbazide, para-benzene-disemicarbazide, toluene-2,4-disemicarbazide, toluene-2,4-disemicarbazide, bis (4-semicarbazido-phenyl)ether, bis (4,4'-hydrozide)-3,3'-dimethoxy biphenyl, di-N,N'-methylamino urea, 4,4'-methylene-bis (cyclohexene semicarbazide), 3-semicarbazide-methyl-3,5,5-trimethylcyclohexyl-semicarbazide [or] and mixtures thereof.

7 (Twice Amended) The process according to claim 4, [characterized, in that] wherein said polysulphonyl hydrazide is selected from the group consisting of p,p'-oxybis benzene sulphonyl hydrazide[,], bis(methylhydrazido)sulphate, bis (methylhydrazidosulphonyl)piperazine, and bis p-(hydrazidosulphonylamino)benzene

9 (Twice Amended) The process according to claim 1, [characterized in that] wherein the material which contains no groups which are reactive towards the compound containing reactive hydrogen, is a polyether, a polyester, a polycarbonate, a polyacrylate, a polyvinylalkylether, a polyurethane, a polyacrylate, a polyvinylalkylether, or a polyurethane [, optionally substituted by substituents which are non reactive towards the material containing reactive hydrogen, and non- or low reactive towards the isocyanate functional material or is a plasticizer of the group of phthalic alkylesters, adipic alkyl esters, sebacic alkyl esters, dodecanoic alkyl esters, polyesters, phosphate esters, fatty esters, straight and modified natural or mineral oils, sulphonated oils, ethoxylated oils, epoxidised oils, fatty acids, sulphon amides, fat liquors, lecithine or a mixture thereof, optionally mixed with water].

10 (Twice Amended) The process according to [claims 1-9, characterized, in that the] claim 1, wherein said mixture of the polyisocyanate functional, the polyepoxy functional, or the polyketone functional compound or polymer and the compound containing reactive hydrogen, is solvent free.

11. (Twice Amended) The process according to [claims 1-10, characterized, in that] claim 1, wherein said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in [a] an equivalent ratio of 0.5 to 1.5, [and preferably in a ratio of 0.9 to 1 1,] applied onto a substrate and the so obtained covered or impregnated substrate is heated to a temperature of 50 to 300° C for 1 to 10 min [and preferably to a temperature of 60 to 200° C for 1 to 5 min].

12. (Twice Amended) The process according to [claims 1-10, characterized, in that] claim 1, wherein said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in [a] an equivalent ratio of 0.5 to 1.5, [and preferably in a ratio of 0,9 to 1,1] and applied onto a substrate whereafter the covered or impregnated substrate is immersed into water of 20 to 100° C for 1 to 10 min.

13 (Twice Amended) Coatings, coated substrates, adhesives, films, sheets, impregnated substrates, synthetic leathers, [inmould] in mold coatings, coated leathers, coated polyvinylchlorides, coated non-wovens, coated coagulated polyurethane substrates, and breathable coated substrates, [characterized, in that they are] obtained by applying the process of [any of the preceding claims 1-14] claim 1.

14. (Twice Amended) A coating mixture to be applied in the process of [claim 1 to 15] claim 1 wherein the coating mixture comprises a mixture of a polyisocyanate functional, a polyepoxyde functional, a polyanhydride functional or a polyketone functional compound and a dispersion of a compound containing reactive hydrogen, which compound is a polyhydrazide, a polysemicarbazide, a polysulphonylhydrazide, carbodihydrazide, in a material which contains no groups which are reactive towards the compound containing reactive hydrogen, in which mixture the reactivities of the [isocyanatee] isocyanate, epoxide, anhydride or the ketone functions towards the hydrazide, semicarbazide sulphonylhydrazide or carbodihydrazide is absent or low at ambient conditions and the reactivities are high at temperatures of 50 to 300° C or when the mixture is immersed into water.

15. (Twice Amended) A coating mixture according to [claims 1-14, characterized, in that] claim 1, wherein the mixture of the polyisocyanate functional compound, the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature for at least one day.

16. (Twice Amended) A coating mixture according to [claims 14 or 15, characterized, in that] claim 14, wherein the mixture of the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature as a one pot system.

17. (Twice Amended) A coating mixture according to [claims 14-16, characterized, in that] claim 14, wherein the compound containing reactive hydrogen is present as a grind which is dispersed in a material which is non-reactive towards the material containing reactive hydrogen

18. (Twice Amended) A coating mixture according to [claims 14-16, characterized, in that] claim 14, wherein at ambient temperature the compound containing reactive hydrogen is a solid, which is a powder, a granule, a flake or a grind or a mixture thereof [, which is preferably ground].

19 (Twice Amended) A coating mixture according to [claims 14-16, characterized, in that] claim 18, wherein [the] particle size of the grind [ground] or of the dispersion of the compound containing reactive hydrogen is from [0,5] 0.5 to 200 μm [, preferably from 0.5 to 60 μm and most preferably from 0.5 to 15 μm].

Process for the preparation of a coating, a coated substrate, an adhesive, a film or sheet, for the thus obtained products and the coating mixture to be used in the process.

The present invention relates to a process to prepare a coating, adhesive, film or sheet, of the thus obtained products and to the coating mixture to be used in the process.

5 Several methods have been developed for high solids or solvent free application in the polyurethane industry to prepare coatings or films.

10 One approach is the reaction of a polyisocyanate or of a isocyanate functional polyurethane prepolymer with a polyol at 160-180°C. In this way flexible coatings can be prepared with a medium strength. A disadvantage of this method is that the potlife of the mixture is limited to about 3 hours.

15 Further, while a reaction within 2 to 3 min is required, there is only a partial reaction within that time and a post reaction takes place between the unreacted components during storage at ambient temperature. As a consequence the coatings are sometimes tacky immediately after the curing and for example a coated piece of textile cannot be rolled up.

20 A second approach is the reaction between a blocked polyisocyanate and a polyamine or polyol. Especially with polyamines strong films can be obtained. When the blocking agent is a ketoxime, such as butanone oxime, it will evaporate during the reaction, but usually some of the butanone oxime will stay in the film. The result is that, also after application, there may be toxic vapours and the coating smells. Other types of blocking agents, such as dimethylpyrazole and triazole types, malonic esters or acetoacetates, and ϵ -caprolactams need a long de-blocking time and they will partially stay in the coating as not-polymerized molecules. Also in these cases the coatings smell.

10

15

20

25

30

35

5

10

20

30

Such a dispersion is obtained by dispersing the material containing reactive hydrogen, in the second mate-

rial by conventional methods which may be by a for example
a disperser or a pearl mill. By dispersing the compound
containing reactive hydrogen in an inert material a smal-
ler particle size and a greater area can be obtained than
5 when the pure solid is ground.

The compound containing reactive hydrogen reacts
fast with a polyisocyanate functional, a polyepoxide func-
tional, a polyanhydride, or a polyketone functional com-
pound or polymer under selected conditions. Such a condi-
10 tion may be a sudden increase of temperature. At that mo-
ment the material containing reactive hydrogen will melt
or dissolve in the system, the reactive sites of the mole-
cules can move freely, and while the mixture is homogeni-
sed by diffusion, the reaction with the polyisocyanate
15 functional, the polyepoxide functional, the polyanhydride
functional, or the polyketone functional compound or poly-
mer occurs.

The homogenisation at higher temperatures will be
more efficient and as a result the reaction will be faster
20 and more complete. Moreover, the performance of the films
or coatings will be better when the particle size of the
material containing reactive hydrogen, is small.

An excellent film or coating quality is obtained
when the particle size is between 0,5 and 200 μm . A more
25 preferable particle size is between 0,5 and 60 μm and the
most preferable size is between 0,5 and 15 μm .

To obtain a maximal potlife, the material contain-
ing reactive hydrogen may not melt or soften in the reac-
tion mixture at ambient temperature.

30 Several types of material containing reactive hy-
drogen may be used in the process such as polyhydrazides,
polysemicarbazides, polysulphonyl hydrazides, carbohydra-
zide, guanidine or guanidine salts, polyamines or polyami-
ne salts.

35 Said polyhydrazide which may be used in the pro-
cess of the invention may be oxalic dihydrazide, malonic
dihydrazide, succinic dihydrazide, adipic dihydrazide, se-
bacic dihydrazide, dodecanoic dihydrazide, isophthalic di-

hydrazide, piperazine N,N'-dihydrazide, m-benzene-dihydrazide, p-benzene-dihydrazide.

Preferably adipic dihydrazide and carbodihydrazide are used since they are inert in the reaction mixtures with an epoxide functional-, an anhydride functional- or a ketone functional compound or polymer at ambient temperature for at least one year. They further reacts instantaneously with a polyisocyanate, a polyepoxide, a polyanhydride or a polyketone functional compound or polymer at temperatures of 80-180°C or higher.

A polysemicarbazide which may be used in the process of the invention is selected from ethane-disemicarbazide, butane-disemicarbazide, propane-disemicarbazide, hexane-disemicarbazide, para-benzene-disemicarbazide, toluene-2,4-disemicarbazide, bis (4-semicarbazido-phenyl)ether, bis (4,4'-hydrazido)-3,3'-dimethoxy biphenyl, di-N,N'-methylamino urea, 4,4'-methylene-bis(cyclohexene semicarbazide), 3-semicarbazido-methyl-3,5,5-trimethylcyclohexyl-semicarbazide or mixtures thereof.

A polysulphonylhydrazide which may be used in the process of the invention is selected from p,p'-oxybis benzene sulphonyl hydrazide; bis(methylhydrazido)sulphate, bis (methylhydrazidosulphonyl)piperazine, or bis p-(hydrazidosulphonylamino)benzene.

Usually, guanidine hydrochloride, guanidine acetate, guanidine carbonate and guanidine nitrate are suitable a guanidine salts.

A suitable polyamine or polyamine salt may be piperazine, piperazine diacetate, piperazine dihydrochloride, lysine, lysine hydrate, diaminoisophorone diacetate, diaminoisophorone dihydrochloride.

As mentioned before it is preferable when the compound containing reactive hydrogen is used as a dispersion in a material which is inert to both the reactive hydrogen compound and the second reagent of the reaction. This material is preferably a polyether, a polyester, a polycarbonate, a polyacrylate, a polyvinylalkylether, a

polyurethane, optionally substituted by substituents which are non reactive towards the material containing reactive hydrogen, and non- or low reactive towards the isocyanate functional material or is a plasticizer of the group of phthalic alkylesters, adipic alkyl esters, sebacic alkyl esters, dodecanoic alkyl esters, polyesters, phosphate esters, fatty esters, straight and modified natural or mineral oils, sulphonated oils, ethoxylated oils, epoxidised oils, fatty acids, sulphon amides, fat liquors, lecithine or a mixture thereof, optionally mixed with water.

An important aspect of the invention is that a low solvent level can be used during the process, and most preferably the process is solvent free.

In the process of the invention a polyisocyanate functional compound or polymer, a polyketone functional compound or polymer, a polyepoxide functional compound or polymer, or a polyanhydride functional compound or polymer and the material containing reactive hydrogen are mixed together in an stoichiometric ratio of 0.5 to 1.5, and preferably in a ratio of 0.9 to 1.2, whereafter the obtained mixture is applied onto a substrate and the covered or impregnated substrate is heated to a temperature of 50 to 300°C for 1-20 min and preferably to 80 to 200°C for 1 to 10 min.

Surprisingly it appeared that the reaction takes place as well when the polyisocyanate functional compound or polymer and the material containing reactive hydrogen are mixed together in a stoichiometric ratio of 0.5-1.5 and preferably in a ratio of 0.9 -1.1 whereafter the obtained mixture is applied onto a substrate and the covered or impregnated substrate is immersed into water of 20 to 100°C for 0.5 to 10 min.

The isocyanate functional compound or polymer which is used in the process of the invention is usually a polyisocyanate or a isocyanate functional polyurethane prepolymer.

Urea functions are formed by the reaction of the isocyanate functions and the NH_2 -functions of the material containing reactive hydrogen.

5 The ketone functional compound or polymer of the invention is preferably a ketone functional polymer polyurethane with in-chain, pendant and/or terminal ketone functions. Ketimine functions are formed by the reaction of the ketone and the NH_2 -functions of the material containing reactive hydrogen.

10 The anhydride functional compound of the invention is usually a polyanhydride or a copolymer containing anhydride functions. Amide functions are formed by the reaction of the anhydride function and the NH_2 -functions of the the material containing reactive hydrogen.

15 The epoxide functional compound of the invention is usually a polyepoxide or a epoxy functional polymer. The epoxide rings are opened during the reaction with the NH_2 -functions of the material containing reactive hydrogen and secondary or tertiary amines are formed.

20 A further part of the invention are the coatings, coated substrates, adhesives, films, sheets, impregnated substrates, synthetic leathers, inmould coatings, coated leathers, coated polyvinylchlorides, coated non-wovens, coated coagulated polyurethane substrates, breathable coated
25 substrates which are obtained by the process of the invention.

The thus obtained films or coatings are strong, dry, flexible and UV-resistant.

30 The process and application results of the present invention are profitable regarding to conventional heat curable systems which are low-solvent or solvent-free. Regarding to the system in which a polyisocyanate functional compound or polymer reacts with a polyol the mixture of the present invention has a longer pot life,
35 while the reaction is faster, almost instanteneous, and more complete at elevated temperatures. The obtained films or coatings are stronger because in the process of the invention urea functions are formed by the reaction of the

isocyanate function and the amine or hydrazide, while in the reaction of a isocyanate and a OH-function a urethane function is formed. It is wellknown that an urea function gives additional strength because of the presence of hydrogen at the N of the urea function which makes it possible to form hydrogen bridges.

Regarding to the systems in which blocked isocyanates are used in combination with polyamines films or coatings of comparable strength are formed by the process of the invention, but the elongation and the tension at break is larger. The potlife of the mixture of the present invention is longer, there are no evaporating toxic reactants such as butanone oxime, or remaining low molecular material such as dimethylpyrazole and triazole types, malonic esters or acetoacetates and the resulting films or coatings do not smell. As a consequence the process of the invention will not have any damaging effect on the environment.

Regarding to the systems in which a polyisocyanate is reacted with a polyamine from which the amine functions are deactivated by the reaction with a maleic ester under formation of a aspartate, the mixtures of the process of the invention have a much longer potlife.

Regarding to the system in which an incorporated uretdion acts as internal blocking agent the reaction time is much shorter at elevated temperatures.

Finally the invention provides a coating mixture comprising on the one side a isocyanatefunctional compound, a polyepoxide functional compound, a polyanhydride functional compound, or a polyketone functional compound and on the other side a compound containing a reactive hydrogen which is not or low reactive at ambient temperature and highly reactive under selected conditions, which coating mixture is applied in the process of the present invention.

The coating mixture of the invention is stable at ambient temperature for at least one day and preferably the coating mixture of the epoxide functional-, the anhy-

drude functional- or the ketone functional compound or polymer and the compound containing reactive hydrogen is stable at ambient temperature as a one pot system.

The compound containing reactive hydrogen is present in the mixture as a solid, a powder, a granule, a flake or a grind or a mixture thereof and is preferably ground.

As mentioned before it is preferable when the compound containing reactive hydrogen is used as a dispersion in a material which is inert to both the reactive hydrogen compound and the second reagent of the reaction.

The particle size of the ground or of the dispersion of the compound containing reactive hydrogen is from 0,5 to 200 μm , preferably from 0.5 to 60 μm and most preferably from 0.5 to 15 μm .

The mixtures of the isocyanate functional material and the material containing reactive hydrogen, may be applied onto a substrate. They may be used as films, sheets, in adhesives, sealants, printing ink and in coatings. They may be applied on any substrates, including leather or artificial leather, metals, wood, glass, plastics, paper, paper board, textile, non-woven, cloth, foam and the like by conventional methods, including spraying, flow-coating, reverse-coating, brushing, dipping, spreading and the like. The cured material may be further treated with coatings, such as a top-coat, or adhered to any substrate by direct or transfer coating technics.

Many additives may be present for application reasons, for example fillers, colorants, pigments, silicones, fire retardants, matting agents, flow agents, foaming agents and the like.

Some applications where the process of the invention is used are of special interest.

For example, the process may be used for the preparation of a coated textile to be used as a synthetic leather. Such a process may comprise the preparation of an adhesion coat onto textile, followed by applying a mixture of a polyurethane prepolymer and a hydrazide-, semicarba-

zide-, amine or amine salt- dispersion of the invention onto the adhesion coat and curing of this mixture at an elevated temperature, which may be between 80 and 250°C. The coating may further be embossed at 80 to 250°C.

5 By repeating of the process described above on the backside of the textile a double sided coated textile may be obtained.

Alternatively the process may be used for the preparation of a coated substrate to be used as synthetic
10 leather by transfer coating, which may comprise the preparation of a skincoat onto release paper, followed by the preparation of an intermediate coat by applying a mixture of a polyurethane prepolymer and a hydrazide-, semicarba-
zide-, amine or amine salt- dispersion of the invention
15 onto the skincoat and curing of this mixture at an elevated temperature, which may be between 80 and 250°C, whereafter an adhesive coat is applied onto the intermediate coat in which a piece of textile is laminated and the thus obtained material is dried, whereafter the release paper
20 is removed.

The process described above may also be used for the preparation of for example coated leather, coated polyvinyl chloride, coated non-woven, coated coagulated polyurethane substrates.

25 Alternatively the process may be used for the preparation of a coated polyvinyl chloride to be used as synthetic leather by transfer coating, which may comprise the preparation of a skincoat onto release paper, followed by the preparation of an intermediate coat by applying a
30 mixture of a polyurethane prepolymer and a hydrazide-, semicarbazide-, amine or amine salt- dispersion of the invention onto the skincoat and curing of this mixture at an elevated temperature, which may be between 80 and 250°C, whereafter a compact polyvinylchloride substrate onto the
35 high solids coat is prepared by applying a polyvinylchloride paste onto the high-solids coat, optionally followed by laminating of a piece of textile into the polyvinyl-

chloride paste, and curing of the polyvinyl chloride paste.

The process may further be used in the preparation of a moulded material by inmould coating which comprises spraying of a mixture of a polyurethane prepolymer and a hydrazide-, semicarbazide-, amine or amine salt-dispersion of the invention, and optionally a non-reactive solvent into a matrix until a desired coating thickness is obtained. The matrix may be heated during the spray process, or after the spraying process. After the curing the moulded material may be removed.

Various aspects of the present invention are illustrated by the following examples. These examples are only illustrative of the invention and are not limiting the invention as claimed hereafter.

Examples

Example 1

Preparation of an aliphatic polyether based isocyanate functional polyurethane prepolymer.

Under a nitrogen atmosphere 112.78 g (507.56 mmole) of 3-isocyanatomethyl-3,5,5-trimethylcyclohexylisocyanate (hereafter referred to as IPDI) was added to a mixture of 139.21 g (138.24 mmole) of a polypropylene glycol with a molecular weight of 1007, 163.77 g (81.89 mmole) of a propylene glycol with a molecular weight of 2000 and 4.2 g (31.34 mmole) of trimethylol propane at 60-70°C while stirring. The mixture was heated to 100°C and reacted at this temperature for 2 hrs to form a polyurethane prepolymer. After 1 hr of reaction time 0.1 g of tin octoate was added as a catalyst. The reaction mixture was cooled down. The amount of remaining NCO was measured and appeared to be 4.43%.

Example 2

Preparation of an aliphatic polyester based isocyanate functional polyurethane prepolymer.

Under a nitrogen atmosphere a 107.12 g (482 mmole) of IPDI was added to a mixture of 141.81 g (151.67 mmole) of a polyester diol with a molecular weight of 935 available from Occidental as Ruco S 1015-120, 166.83 g (55.61 mmole) of a polyesterdiol with a molecular weight of 3000 available from Occidental as Ruco S 1015-35 and 4.2 g (31.34 mmole) of trimethylol propane at 60-70°C while stirring. The mixture was heated to 100°C and reacted at this temperature for 2 hrs to form a polyurethane prepolymer. After 1 hr of reaction time 0.1 g of tin octoate was added as a catalyst. The reaction mixture was cooled down. The amount of remaining NCO was measured and appeared to be 3.99%.

15

Example 3

Preparation of an aromatic polyether based isocyanate functional polyurethane prepolymer.

The procedure of example 1 was repeated with the exception that the IPDI was replaced by 88.31 g (507.56 mmole) of toluene diisocyanate (hereafter referred to as TDI) and the reaction was executed at 90-95°C. The NCO amount appeared to be 4.60%.

25

Example 4

Preparation of an aromatic polyester based isocyanate functional polyurethane prepolymer.

The procedure of example 2 was repeated with the exception that the IPDI was replaced by 85.61 g (492 mmole) of TDI and the reaction was executed at 90-95°C. The NCO amount appeared to be 4.23%.

Example 5

Preparation of a ketone functional polyurethane polymer from a isocyanate functional polyurethane prepolymer and hydroxyacetone

Under a nitrogen atmosphere a mixture of 100 g of the polyurethane prepolymer from example 1 and 7.81 g (105.48 mmole) of hydroxyacetone were heated to 100°C. The

1 mixture was stirred for 2 hrs at 100°C. After 1 hr of re-
2 action time 0.1 g of tinocatoate was added as a catalyst.
3 The disappearance of NCO was checked by IR-spectroscopy by
4 following the NCO signal at 2269 cm⁻¹.

5

Example 6

Preparation of a ketone functional polyurethane
polymer.

Under a nitrogen atmosphere 68.42 g (308 mmole)
10 of IPDI was added to 251 g (171 mmole) of a ketone functi-
onal polyester diol obtainable from NeoResins as PEC 205
in 80 g of dipropylene glycole dimethyl ether at 60°C whi-
le stirring. The mixture was heated to 100°C and reacted
at this temperature for 2 hrs to form a polyurethane pre-
15 polymer. After 1 hr of reaction time 0.1 g of tinocatoate
was added as a catalyst. The reaction mixture was cooled
down. The amount of remaining NCO was measured using a
sample of 10 g, and appeared to be 2.71.

18.65 g (252 mmole) of methoxyethylamine was added
20 to the obtained polyurethane prepolymer and the mixture
was stirred for 15 min at 20°C. The disappearance of NCO
was checked by IR-spectroscopy by following the NCO signal
at 2269 cm⁻¹.

25 Example 7

Preparation of a ketone functional polyurethane
polymer from a isocyanate functional isocyanurate and hy-
droxyacetone

Under a nitrogen atmosphere a mixture of 151 g
30 (259 mmole) N,N',N''-triisocyanatohexylisocyanurate and
57.50 g (777 mmole) of hydroxyacetone in 52.13 g of dipro-
pylene glycol dimethyl ether were heated to 90°C. The mix-
ture was stirred for 2 hrs at 90°C. After 1 hr of reaction
time 0.1 g of tinocatoate was added as a catalyst. The dis-
35 appearance of NCO was checked by IR-spectroscopy by follo-
wing the NCO signal at 2269 cm⁻¹.

Example 8

Comparative example: preparation of a film from a MEK-oxime blocked polyurethane polymer and a amine functional crosslinker.

5 9.39 g (105.48 mmole) of mekoxime was added to
100 g of the prepolymer of example 1 at 60-65°C. The mixture was stirred for 2 hrs at 70°C. The disappearance of the NCO was checked by the absence of the NCO-signal in the Infrared spectrum at 2270 cm⁻¹. The product was cooled
10 down and mixed with 12.47 g (52.4 mmole) of 3,3'-dimethyl-4,4'-diamino-dicyclohexyl-methan and 0.1 g of a 10 % solution of dibutyltinlaureate in dipropylene glycol dimethyl ether as catalyst.

200 µm films were prepared and cured at 180°C for
15 5 min.

Example 9

Comparative example: preparation of a film from a OH-functional polyurethane polymer and a NCO-crosslinker

20 A: preparation of the OH-functional polyurethane polymer:

Under a nitrogen atmosphere 264 g (132 mmole) of a polypropyleneglycol with a molecular weight of 2000 and 7.92 (88 mmole) of 1,3-butanediol were heated to 80°C.
25 97.68 (440 mmole) of IPDI was added and the mixture was stirred for 2 hrs at 100°C. After 1 hr of reaction time 0.1 g of tinocatoate was added as a catalyst. The reaction mixture was cooled down and the amount of remaining NCO in the resulting prepolymer was determined by titration and
30 appeared to be 4.6%. 36.21 g (402 mmole) of 1,3- butanediol and 0.1 g of dibutyl tinlaureate were added and the mixture was heated to 100° for two hrs. The disappearance of the NCO was checked by the absence of the NCO-signal in the Infrared spectrum at 2270 cm⁻¹. The product was cooled
35 down and had an OH-amount of 2.13 meq/g

B: preparation of an NCO-crosslinker: 14.4 g (240 mmole) of n-propanol was added within 30 min to 102.2 gr (containing 600 mmole of NCO) of N,N',N''-triisocyanato-

hexylisocyanurate, whereafter the mixture was stirred and heated at 80° for 2 hrs . After 1 hr of reaction time 0.1 g of tinocatoate was added as a catalyst. The reaction mixture was cooled down and the amount of remaining NCO in the resulting polymer was determined by titration and appeared to be 12.0

A 200 μ m film was prepared from a mixture of 13 gr of the product of A and 9.2 g of the product of B with 0.05 g of a 10 % solution of dibutyltinlaureate in dipropylene glycol dimethyl ether as catalyst. The film was cured for 5 min at 160°C.

Example 10

Preparation of a semicarbazide from 4,4'-methylene-bis(cyclohexylisocyanate) and hydrazine.

26.2 g (100 mmole) of 4,4'-ethylenebis(cyclohexylisocyanate) in 26.2 g of dipropylene glycol dimethyl ether was added to 12 g (240 mmole) of hydrazine hydrate in 18 g of isopropanol and 12 g of of dipropylene glycol dimethyl ether while keeping the temperature below 25°C by cooling with ice. A white precipitate appeared. After stirring for 30 min the precipitate was filtered of and rinsed with dipropylene glycol dimethyl ether. The product was dried at 80°C. The yield was 44.42 g = 88.9 % from the theoretical amount.

Example 11

Preparation of a semicarbazide from hexamethylene diisocyanate and hydrazine.

33.6 g (200 mmole) of hexamethylenediisocyanate in 33.6 g of dipropylene glycol dimethyl ether was added to 24 g (480 mmole) of hydrazinehydrate in 27 g of isopropanol and 24 g of of dipropylene glycol dimethyl ether while keeping the temperature below 25°C by cooling with ice. A white precipitate appeared. After stirring for 30 min the precipitate was filtered of and rinsed with dipropylene glycol dimethyl ether. The product was dried at

80°C. The yield was 41.95 g = 84.9 % from the theoretical amount.

Example 12

5 Preparation of a semicarbazide from a commercial mixture of toluene diisocynate and hydrazine.

34.8 g (200 mmole) of a commercial mixture of toluene diisocynate in 33.6 g of dipropylene glycol dimethyl ether was added to 24 g (480 mmole) of hydrazine hydrate
10 in 24 g of isopropanol and 24 g of water while keeping the temperature below 25°C by cooling with ice. A white precipitate appeared. After stirring for 30 min the precipitate was filtered of and rinsed with dipropylene glycol dimethyl ether. The product was dried at 80°C.

15 The yield was 34.78 g = 69.3 % from the theoretical amount.

Example 13

20 Preparation of a semicarbazide from 3-isocyanatomethyl-3,5,5-trimethylcyclohexylisocyanate and hydrazine.

44.4 g (200 mmole) of IPDI in 33.6 g of dipropylene glycol dimethyl ether was added to 24 g (480 mmole) of hydrazine hydrate in 24 g of isopropanol and 24 g of water while keeping the temperature below 25°C by cooling
25 with ice. The mixture was stirred for 1 hr and the solvents were evaporated. The mixture was cristalized from isopropanol.

Example 14

30 Preparation of a grind and of a dispersion of adipic dihydrazide.

Adipic dihydrazide was ground as a pure powder or it was ground in a 1:1 weight ratio in di(ethylhexyl) adipate in the presence of 0.5 % of Triton X-100. By increasing the dispersioning time and the speed of the stirring
35 blade smaller particle sizes could be obtained. The grinds and dispersions which were obtained are presented in

Table I. The range of the particle size in the dispersions were measured by microscopy

5 *Table 1 Particle sizes of adipic dihydrazide in a pure grind or as a dispersion in di(ethylhexyl) adipate*

Example	medium	particle size of adipic dihydrazide in the medium (μm)
		Range
14 A	Pure	30-300
14 B	pure, ground	30-250
14 C	di(ethylhexyl)adipate	40-150
14 D	di(ethylhexyl)adipate	30- 60
14 E	di(ethylhexyl)adipate	5- 40
14 F	di(ethylhexyl)adipate	0.5-13

Example 15

10 Preparation of a dispersion of adipic hydrazide in different liquid materials which are none non-reactive towards the adipic dihydrazide.

Adipic hydrazide was dispersed in a 1:1 weight ratio in liquid materials which were non-reactive towards
 15 the adipic dihydrazide in the presence of 0.5 % of Triton X-100 by a Dispermat pearl mill configuration for 1.5 hrs at 5000 rpm. The range of the particle size in the dispersions depending on the medium were measured by microscopy. The results are presented in Table 2. The results show
 20 that the values for the particle size in a more polar medium are slightly less than in an apolar medium.

Table 2 Particle size of adipic dihydrazide as dispersion in several media

25

Example	medium	particle size of adipic dihydrazide in the medium (μm)
		range
15A	di(ethylhexyl)adipate	30 - 60
15B	dibutyl phthalate	30 - 60
15C	dioctyl phthalate	30 - 60
15D	dibutyl sebacate	30 - 60
15E	polyethylene glycol	10 - 30
15F	tributoxyethylphosphate	10 - 30
15G	soybean lecithin	10 - 30
15H	castor oil	10 - 30
15I	N-methyl pyrrolidone	10 - 30
15J	dipropylene glycol	10 - 30
	dimethylether	

Example 16

Preparation of a dispersion of several dihydrazides, disemicarbazides, a di(sulphonylhydrazide), amine salts.

Several dihydrazides, disemicarbazides, sulphonyldihydrazides and diamine salts were ground in di(ethylhexyl) adipate or in tributoxyethyl phosphate or in N-methylpyrrolidone by a Dispermat pearl mill configuration for 1.5 hrs at 5000 rpm. The products which were ground were: carbodihydrazide, oxalic dihydrazide, succinic dihydrazide, adipic dihydrazide, sebacic dihydrazide, dodecanoic dihydrazide, isophthalic dihydrazide, the products of example 10, 11, 12 and 13, 4,4'-oxybis(benzenesulphonylhydrazide), guanidine hydrochloride, lysine.

In all cases the particle sizes of the hydrogen reactive materials in the dispersions were measured by microscopy. The ranges in di(ethylhexyl) adipate were comparable and were between 30 and 60 μm . The values in tributoxyethyl phosphate or in N-methylpyrrolidone were slightly less and were 10-30 μm .

Example 17

Kinetics of the curing of the prepolymers of example 1, 2, 3 and 4 with adipic dihydrazide at several temperatures and times, measured by infrared spectroscopy.

The reaction of the prepolymers of example 1, 2, 3 and 4 with the adipic hydrazide dispersion of example 15 A (containing 5.716 meq of hydrazide/g) was followed at several temperatures by infrared spectroscopy. Further the potlife of the mixtures at 50°C were controlled.

50 gr of a polyurethane prepolymer of example 1, 2, 3, or 4 was mixed with a stoichiometric amount of the adipic dihydrazide dispersion and a film was prepared onto a sodium chloride cell. An Infrared spectrum was prepared which showed a large NCO signal at 2260 cm^{-1} . The cell was heated at 140, 160 or at 180°C for several minutes and the

The results show that the IPDI-based prepolymers from example 1 and 2 are more reactive than the TDI-based prepolymers from example 3 and 4, which is indicated by a faster disappearance of the NCO-signal. There is not a significant difference in reactivity between the polyether and the polyester prepolymers.

Further the mixtures were stable for at least 6
10 weeks at 50°C and at that moment the intensity of the sig-
nals of the NCO in the IR-spectrum were comparable with
that of the freshly prepared mixtures.

Table 3 decrease of the NCO signal in the infrared spec-
trum during the curing reaction of isocyanate functional
prepolymers of example 1, 2, 3 and 4 with an adipic acid
dispersion in di(ethylhexyl) adipate

Product of Example	Curing Temperature (°C)	amount of remaining NCO (%) after ^a			
		4 min	6 min	9 min	15 min
1	140	19.0	5.7	2.5	1.2
	160	1.5	0.3	0	0.3
2	140	26.5	5.9	2.2	1.2
	160	1.2	0.1	0	0
3	140	na	78.9	55.9	49.6
	160	na	25.2	10.3	8.2
	180	17.4	9	5.5	2.2
	200	3.2	1.5	1.0	0.7
4	140	na	89.0	58.8	51.1
	160	na	49.7	11.5	8.5
	180	19.4	9.8	5.6	2.4
	200	5.4	2.7	1.5	1.2

Notes to table 3:

25 a) determined by measuring the area of the signal at 2260-70 cm^{-1} from the NCO-signal regarding to the carbonyl signal at 1740 cm^{-1} .

b) na = not available

Example 18

Kinetics of the film formation by curing of the polyurethane prepolymer of example 2 and 4 with adipic dihydrazide or carbodihydrazide at several temperatures and times.

50 gr of polyurethane prepolymer of example 2 (based on IPDI, which is an alifatic diisocyanate) or 4 (based on TDI, which is an aromatic diisocyanate) were mixed with an stoichiometric amount of the adipic dihydrazide dispersion of example 15 A or of the carbodihydrazide dispersion of example 16 and the mixtures were applied on-to release paper. The curing of the films was checked at 120, 140 and at 160°C at 1, 2, 3, 6 and 12 min. The results are presented in tabel 4. Both, aromatic and aliphatic prepolymers are completely reacted with the carbodihydrazide or with the adipic dihydrazide after 3 min. at 160°C. Regarding to example 17 the reaction is faster because the sodium chloride cell needs more time for warming up than release paper. When the film formation was complete flexible films were obtained.

Table 4: Film formation by curing of a polyurethane prepolymer of example 2 and 4 with adipic dihydrazide or carbodihydrazide at several temperatures and times

poly-urethane of example	hydrogen reactive material	curing temp. (°C)	phase of the film ^{a)} at a curing time of				
			1 min	2 min	3 min	6 min	12 min
2	adipic dihydrazide	120	w	w	w	t	r
		140	t	r-i	r	r	r
		160	r-i	r	r	r	r
2	carbodi-hydrazide	120	w	w	t	t	r
		140	t	t	r-i	r	r
		160	r-i	r	r	r	r
4	adipic dihydrazide	140	w	w	w	w	t
		160	r-i	r	r	r	r
4	carbodi-hydrazide	140	r-i	r	r	r	r
		160	r-i	r	r	r	r

Notes to Table 4

a) w : the mixture is still wet; no reaction is observed

t : the mixture is tacky; a partial reaction is effected

r-i : film formation is effected, but the film is not strong, which means that the reaction is incomplete

r : complete film formation is effected

Example 19

Preparation of films by curing a prepolymer of example 2 and adipic hydrazide powder or dispersion of example 14 and measurement of the homogeneity of the films depending on the particle size of the adipic dihydrazide.

3.48 g (20 mmole) of ground adipic dihydrazide or 7.00 g (20 mmole) of an adipic dihydrazide dispersion in di(ethylhexyl)adipate of example 15 A was stirred into 50 g (containing 40 meq of NCO) of the prepolymer of example 2. Films of 200 μ m were prepared onto a black coated glossy paper and heated for 3 min at 160°C. The gloss of the films was measured by a reflectometer. Further films of 200 μ m were prepared on transparant polyester sheets and the transparency of the films was determined by measuring the transmission by spectroscopy at 550 nm on a Hitachi model 101 spectrophoto-meter. The gloss and the transparency of the films is a measure for the homogeneity of the films. The results of the tests are in table 5. It appeared that when the particle size of the adipic dihydrazide was small, the gloss and the transparency of the films were maximal.

Table 5: Homogeneity of cured films depending on the particle size of the adipic dihydrazide

Adipic hydrazide grind originated from example	particle size of the adipic dihydrazide in the grind (μ m)	gloss of cured films of 200 μ m	transmission of cured films of 200 μ m(%)
	range		
14 A	30 - 300	7.8	52.2
14 B	30 - 250	8.5	64.5
14 C	40 - 150	27	85.0
14 D	30 - 60	46	93.5
14 E	5 - 40	60	94.6
14 F	0.5 - 13	95	97.0

is the ultimate tensile strength just before the film breaks. The elongation is the maximal elongation before the film breaks.

5 Example 21

Preparation of coatings on glass by curing a polyisocyanate and the adipic hydrazide dispersion of example 15A.

50 g of N,N',N''- tris(6-isocyanatohexyl)isocyanurate or of, N,N'-bis(6-isocyanato-hexyl-N-(6-isocyanato-hexylamido)urea was mixed with a stoichiometric amount of the adipic hydrazide dispersion of example 15A or of the carbodihydrazide dispersion of example 16. 200 µm films were prepared on glass and heated for 6 min at 160°C. Hard coating surfaces were obtained with a good adhesion to the glass.

 Example 22

Preparation of a film by curing a polyurethane prepolymer and a dispersion of a hydrogen reactive material of example 16.

50 g of the polyurethane prepolymer of example 2 was mixed with a stoichiometric amount of the dispersions of example 16 and the mixtures were applied onto release paper. The curing of the films was checked at 140 or 160°C after 3 min and after 12 min. When no film formation was observed the curing was checked at 220 and 250°C. The results are presented in tabel 7.

The results show that the dihydrazides, disemicarbazides and some diamine salts react with a isocyanate functional polyurethane prepolymer to form a film. These films are flexible. The table further shows that the reactivity of the used dihydrazides is comparable with that of the sulphonyldihydrazide used and both are more reactive than the semicarbazides used. The amine salts need a prolonged heating at higher temperatures before they react.

Table 7: Film formation by curing the polyurethane prepolymer of example 2 and a dihydrazide, disemicarbazide, and a diamine

Hydrogen reactive material	phase of the film ^{a)} at a curing temperature and time of						
	140°C		160°C		220°C		250°C
	3 min	12 min	3 min	12 min	3 min	12 min	3 min
carbodihydrazide	r-i	r	r	r	--	--	--
oxalic dihydrazide	t	r	r	r	--	--	--
succinic dihydrazide	t	r	r	r	--	--	--
adipic dihydrazide	r	r	r	r	--	--	--
sebacic dihydrazide	r	r	r	r	--	--	--
dodecanoic dihydrazide	r	r	r	r	--	--	--
isophthalic dihydrazide	r	r	r	r	--	--	--
4,4'-methylenebis- (cyclohexylisemicarbazide)	w	w	w	t	r	--	--
hexamethylene disemicarbazide	w	w	t	r	r	--	--
tolyldisemicarbazide	w	w	w	t	r	--	--
3-semicarbazidomethyl-3,5,5- trimethylcyclohexylsemi- carbazide 4,4'-oxybis- (benzenesulphonylhydrazide)	r	r	r	r	--	--	--
guanidinehydrochloride	w	w	w	w	w	r	r-i
lysine	w	w	w	w	t	r	r-i

Notes to Table 7

a) w : the mixture is still wet; no reaction is observed

t : the mixture is tacky; a partial reaction is effected

r-i : film formation is effected, but the film is not strong, which means that the reaction is incomplete

r : complete film formation is effected

Example 23

Preparation of a film by curing a polyepoxide and a adipic dihydrazide or a carbodihydrazide dispersion

50 g (138.7 mmole) of Tetrad-X, which is a polyepoxide material obtainable from Mitsubishi, was mixed with a stoichiometric amount of the adipic hydrazide dispersion of example 15 A or the carbodihydrazide of example 16. The products were applied onto release paper and heated at 140 and at 160°C. The mixtures were cured after 6 min at 160°C or after 3 min at 180°C. Brittle films were obtained.

Example 24

Preparation of a film by curing a poly ketone functional compound and a adipic dihydrazide dispersion or a carbohydrazide dispersion.

5 The products of example 5, 6 and 7 and a mixture
20 % of example 7 + 80 % of example 5 were mixed with a
stoichiometric amount of the adipic dihydrazide dispersion
of example 15 A or with the carbodihydrazide dispersion of
example 16. The products were applied onto release paper.
10 The films were cured at 160°C during 3 min. The film for-
mation was complete. The films of the cured product of
examples 5 and 6 were very soft, sticky and flexible. The
film of the cured mixture was flexible and the film of the
cured product of example 7 was very hard.

15

Example 25

Preparation of a film by curing a polyanhydride
functional compound and a adipic dihydrazide dispersion.
20 gr of the styrene/anhydride copolymers, known as SMA
20 1000, SMA-2000 and SMA 3000 obtainable from Elf Atochem
were mixed with 8 g of 1-methoxy-propanol at 80°C until
the mixtures were dissolved. The solutions were cooled
down and mixed with a stoichiometric amount of the adipic
dihydrazide dispersion of example 15 A or with the carbo-
25 hydrazide dispersion of example 16 and applied onto glass
or onto release paper. The mixtures were cured at 160°C
for 6 min onto glass or for 4 min onto release paper. The
coatings obtained were extremely hard and brittle.

30

Example 26

Preparation of a coated textile to be used as
synthetic leather.

A coated textile was prepared by direct coating
comprising:

- 35 - Preparation of an adhesion coat onto textile: 150 µm of
a mixture of 100 g RU-4049, 0.7 g of RM-4456, 5.0 g of
XR-5580 and 5 g water (products obtainable from

Stahl Holland) was applied onto textile by knife over roll and the coated textile was dried for 3 min at 80°C.

- Preparation of a coat from a solvent free material onto the thus obtained coated textile: 400 μ of a mixture of 100 g of the product of Example 1 and 21 g of the adipic hydrazide dispersion of example 15 A was applied onto the coated textile. The coating was cured in an oven at 160° for 3 min.
- The coating was embossed at 190°C.

Example 27

Preparation of a double sided coated textile which may be used as synthetic leather.

A double sided coated textile was prepared by direct coating by repeating the procedure of example 26 onto the other side of the textile.

Example 28

Preparation of a coated textile to be used as synthetic leather by transfer coating.

A coated textile was prepared by transfer coating comprising:

- Preparation of a topcoat onto release paper: 150 μ m of a 1:1 mixture of RU-3952 and RU3953 (both are aqueous polyurethane dispersions obtainable from Stahl Holland) containing 10 % of PP-3215 (a black pigment obtainable from Stahl Holland) was applied onto release paper by knife over roll and the coated paper was dried at 80°C for 3 min.
- Preparation of an intermediate coat from a solvent free material onto the coated release paper: 400 μ m of a mixture of 100 g of the product of Example 1 and 21 g of the adipic hydrazide dispersion of example 15 A was applied onto the topcoat. The coating on the paper was cured in an oven at 160° for 3 min.
- Preparation of an adhesive coat onto the obtained intermediate coat: 150 μ m of SU-6241 (which is a solvent based polyurethane obtainable from Stahl Holland) contain-

ning 5 % of XR-8041 (which is a crosslinker obtainable from Stahl Holland) was applied onto the intermediate coat.

- 5 - A piece of textile was laminated into the adhesive and the thus obtained material was dried at 120°C for 2 min.
- The release paper was removed from the thus coated textile.

Example 29

10 Preparation of a coated materials by transfer coating.

The procedure of example 28 was repeated with the exception that the textile was replaced by leather, non-woven or a coagulated polyurethane substrate.

15

Example 30

Preparation of a coated polyvinylchloride to be used as synthetic leather by transfer coating.

- 20 - Preparation of a skincoat onto release paper: 150 μm of EX-51-550 (a solvent based polyurethane dispersions obtainable from Stahl Holland) was applied onto release paper by knife over roll and the coated paper was dried at 80°C for 3 min.
- 25 - Preparation of a coat from a high solids material onto the coated release paper: 400 μm of a mixture of 100 g of the product of Example 2 and 17 g of the adipic hydrazide dispersion of example 15 A was applied onto the topcoat. The coating on the paper was cured in an oven at 160° for 3 min
- 30 - Preparation of a compact polyvinylchloride substrate onto the high solids coat: 400 μm of a polyvinylchloride paste was applied onto the high-solids coat.
- a piece of textile was laminated in the polyvinyl chloride paste and the polyvinyl chloride was cured by 2 min
- 35 at 160°C followed by 1 min at 220°C.
- the release paper was removed from the thus coated polyvinylchloride on textile.

Example 31

Preparation of a moulded material by inmould coating.

A mixture of 100 g of example 2, 20 g of
5 N,N',N''- tris(6-isocyanatohexyl)isocyanurate and 37 g of
the adipic hydrazide dispersion of example 15 A was diluted
with 50 g of butylacetate and heated to 50°C while
mixing. The mixture was sprayed into a metallic matrix until
a coating of about 400 μm was obtained; the matrix was
10 pretreated with a silicon and was heated at 180°C during
the spray process. The matrix was cooled down and the
moulded material was removed.

CLAIMS

1. The process for the preparation of a coating, adhesive, film or sheet characterized, in that a mixture of a polyisocyanate functional, a polyepoxide functional, a polyanhydride functional or a polyketone functional compound or polymer and a compound containing reactive hydrogen, in which the compound containing reactive hydrogen is dispersed in a material which is non-reactive towards the compound containing reactive hydrogen, which mixture is not or low reactive at ambient conditions and high reactive under selected conditions, is applied onto a substrate at ambient temperature, followed by reacting the above compounds at elevated temperatures.

2. The process according to claim 1, characterized, in that at ambient temperature said compound containing reactive hydrogen is a solid material, a powder, a granule, a flake or grind or a mixture thereof which is preferably ground.

3. The process according to claims 1 and 2, characterized, in that the actual size of the grind of said compound containing reactive hydrogen, is from 0.5 to 200 μm and is preferably from 0.5 to 60 μm and is more preferably from 0,5 to 15 μm .

4. The process according to claims 1 to 3, characterized, in that said compound containing reactive hydrogen is a polyhydrazide, a polysemicarbazide, a polysulphonyl hydrazide, guanidine or a guanidine salt, a polyamine or blocked polyamine or is carbodihydrazide.

5. The process according to claim 4, characterized, in that said polyhydrazide is oxalic dihydrazide, malonic dihydrazide, succinic dihydrazide, adipic dihydrazide, sebacic dihydrazide, dodecanoic dihydrazide, isophthalic dihydrazide, piperazine N,N'-dihydrazide, m-benzene-dihydrazide, p-benzene-dihydrazide.

6. The process according to claims 4 or 5, characterized, in that the polyhydrazide is adipic dihydrazide or carbodihydrazide.

5 zed, in that said polysemicarbazide is ethane-disemicarbazide, butane-disemicarbazide, propane-disemicarbazide, hexane-disemicarbazide, para-benzene-disemicarbazide, toluene-2,4-disemicarbazide, toluene-2,4-disemicarbazide, bis (4-semicarbazido-phenyl)ether, bis
10 (4,4'-hydrazido)-3,3'-dimethoxy biphenyl, di-N,N'-methylamino urea, 4,4'-methylene-bis(cyclohexene semicarbazide), 3-semicarbazido-methyl-3,5,5-trimethylcyclohexyl-semicarbazide or mixtures thereof.

8. The process according to claim 4, characterized,
15 zed, in that said polysulphonyl hydrazide is p,p'-oxybis benzene sulphonyl hydrazide; bis(methylhydrazido)sulphate, bis (methylhydrazidosulphonyl)piperazine, bis p-(hydrazidosulphonylamino)benzene.

9. The process according to claim 4, characterized,
20 zed, in that the guanidine salt is guanidine hydrochloride, guanidine acetate, guanidine carbonate, guanidine nitrate.

10. The process according to claim 4, characterized,
25 zed, in that the polyamine or polyamine salt is piperazine, piperazine diacetate, piperazine dihydrochloride, lysine, lysine hydrate, diaminoisophorone diacetate, diaminoisophorone dihydrochloride.

11. The process according to claim 1, characterized,
30 zed, in that the material of claim 1 which is non-reactive towards said compound containing reactive hydrogen, is a polyether, a polyester, a polycarbonate, a polyacrylate, a polyvinylalkylether, a polyurethane, optionally substituted by substituents which are non reactive towards the material containing reactive hydrogen, and non- or low reactive
35 towards the isocyanate functional material or is a plasticizer of the group of phthalic alkylesters, adipic alkyl esters, sebacic alkyl esters, dodecanoic alkyl esters, polyesters, phosphate esters, fatty esters, straight

and modified natural or mineral oils, sulphonated oils, ethoxylated oils, epoxidised oils, fatty acids, sulphon amides, fat liquors, lecithine or a mixture thereof, optionally mixed with water.

5 12. The process according to claims 1-11, characterized, in that the said mixture of the polyisocyanate functional, the polyepoxy functional, or the polyketone functional compound or polymer and the compound containing reactive hydrogen, is solvent free.

10 13. The process according to claims 1-12, characterized, in that said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in a stoichiometric ratio of 0.5 to 1.5, and preferably in a ratio of 0.9 to 1,1, applied onto
15 a substrate and the so obtained covered or impregnated substrate is heated to a temperature of 50 to 300 °C for 1 to 20 min and preferably to a temperature of 80 to 200 °C for 1 to 10 min.

20 14. The process according to claims 1-12, characterized, in that said polyisocyanate functional compound or polymer and said compound containing reactive hydrogen are mixed together in a equivalent ratio of 0.5 to 1.5, and preferably in a ratio of 0,9 to 1,1, and applied onto a substrate whereafter the covered or impregnated substrate
25 is immersed into water of 20 to 100 °C for 1 to 10 min.

30 15. Coatings, coated substrates, adhesives, films, sheets, impregnated substrates, synthetic leathers, inmould coatings, coated leathers, coated polyvinylchlorides, coated non-wovens, coated coagulated polyurethane substrates, breathable coated substrates, characterised, in that they are obtained by applying the process of any of the preceeding claims 1-14.

35 16. A coating mixture comprising a mixture of a polyisocyanate functional compound, a polyepoxide functional compound, a polyanhydride functional compound or a polyketone functional compound, and a compound containing reactive hydrogen which is not or low reactive at ambient temperature and highly reactive under selected conditions,

which coating mixture is applied in the process of claim 1 to 15.

17. A coating mixture according to claims 1-16, characterized, in that the mixture of the polyisocyanate functional compound, the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature for at least one day.

18. A coating mixture according to claims 16 or 17, characterized, in that the mixture of the polyepoxide functional compound, the polyanhydride functional compound or the polyketone functional compound or polymers thereof and the compound containing reactive hydrogen is stable at ambient temperature as a one pot system.

19. A coating mixture according to claims 16-18, characterized, in that the compound containing reactive hydrogen is present as grind which is dispersed in a material which is non-reactive towards the material containing reactive hydrogen.

20. A coating mixture according to claims 16-18, characterized, in that at ambient temperature the compound containing reactive hydrogen is a solid, which is a powder, a granule, a flake or a grind or a mixture thereof, which is preferably ground.

21. A coating mixture according to claims 16-18, characterized, in that the particle size of the ground or of the dispersion of the compound containing reactive hydrogen is from 0,5 to 200 μm , preferably from 0.5 to 60 μm and most preferably from 0.5 to 15 μm .

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 April 2001 (05.04.2001)

PCT

(10) International Publication Number
WO 01/23451 A2

(51) International Patent Classification⁷: C08G 18/00

(74) Agent: KUPECZ, Arpad; Octrooibureau Los en Stigter
B.V., Weteringschans 96, NL-1017 XS Amsterdam (NL).

(21) International Application Number: PCT/NL00/00699

(22) International Filing Date:
29 September 2000 (29.09.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
1013179 30 September 1999 (30.09.1999) NL

(71) Applicant (for all designated States except US): STAHL
INTERNATIONAL B.V. [NL/NL]; Sluisweg 10,
NL-5145 PE Waalwijk (NL).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,
DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,
RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— Without international search report and to be republished
upon receipt of that report.

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(72) Inventors; and

(75) Inventors/Applicants (for US only): HESSELMANS,
Laurentius, Cornelius, Josephus [NL/NL]; Vughterstraat
151/b, NL-5211 GB 's Hertogenbosch (NL). SPEK,
Dirk, Pieter [NL/NL]; Hoog Meeuwen 19, NL-4268 GT
Meeuwen (NL).

(54) Title: PROCESS FOR THE PREPARATION OF A COATING, A COATED SUBSTRATE, AN ADHESIVE, A FILM OR SHEET, FOR THE THUS OBTAINED PRODUCTS AND THE COATING MIXTURE TO BE USED IN THE PROCESS

(57) Abstract: The invention comprises a process for the preparation of a coating, adhesive, film or sheet. In this process a mixture of a polyisocyanate functional, a polyepoxide functional, a polyanhydride functional or a polyketone functional compound or polymer and a compound containing reactive hydrogen, in which the compound containing reactive hydrogen is dispersed in a material which is non-reactive towards the compound containing reactive hydrogen, which mixture is not or low reactive at ambient conditions and high reactive under selected conditions, is applied onto a substrate at ambient temperature, followed by reacting the above compounds at elevated temperatures. At ambient temperature said compound containing reactive hydrogen is a solid material, a powder, a granule, a flake or grind or a mixture thereof which is preferably ground. The invention comprises further the coating mixtures to be used in the process and the coatings, coated substrates, adhesives, films, sheets, impregnated substrates, synthetic leathers, inmould coatings, coated leathers, coated polyvinylchlorides, coated non-wovens, coated coagulated polyurethane substrates, breathable coated substrates, obtained by applying the process.

WO 01/23451 A2

Docket No
30394-1068

US 44805 WO-kp/co

Declaration and Power of Attorney For Patent Application

English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled
PROCESS FOR THE PREPARATION OF A COATING, A COATED SUBSTRATE, AN ADHESIVE, A FILM OR SHEET, FOR THE THUS OBTAINED PRODUCTS AND THE COATING MIXTURE TO BE USED IN THE PROCESS

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on March 29, 2002 as United States Application No. or PCT International Application Number 10/089,423 and was amended on _____

(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Not Claimed


PCT/NL00/00699
(Number)
1013179
(Number)
(Number)

PCT
(Country)
Netherlands
(Country)
(Country)

29 September 2000
(Day/Month/Year Filed)
30 September 1999
(Day/Month/Year Filed)
(Day/Month/Year Filed)

☐
☐
☐

I hereby certify that this paper is being deposited with
the United States Postal Service on **March 29, 2002**,
in an envelope as "Express Mail Post Office to Addressee"
mailing Label No **EV003481995US** addressed to Box PCT,
Commissioner for Patents, Washington, D C 20231


Annette M. Turk, Legal Assistant

March 29, 2002
(Date)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Laurentius Cornelius Josephus Hesselmans .
and Dirk Pieter Spek

Serial No.: UNKNOWN

Examiner. UNKNOWN

Priority claimed to PCT/NL00/00699

Filed: Herewith (March 29, 2002)

Group Art Unit: UNKNOWN

For. PROCESS FOR THE PREPARATION OF A
COATING, A COATED SUBSTRATE, AN ADHESIVE
A FILM OR SHEET, FOR THE THUS OBTAINED
PRODUCTS AND THE COATING MIXTURE TO BE
USED IN THE PROCESS

ASSOCIATE POWER OF ATTORNEY

Box: PCT

Commissioner for Patents
Washington, D.C. 20231

Dear Sir:


Jeffrey D. Myers, a principal attorney in the above-identified application for Letters Patent, hereby
appoints:

Deborah A. Peacock, Reg. No. 31,649
Paul Adams, Reg. No. 21,096
Rod D. Baker, Reg. No. 35,434
Andrea L. Mays, Reg. No. 43,721;
Stephen A. Slusher, Reg. No. 43,924 and
Katy C. Fain, Reg. No. 42,520

as associate attorneys with full power

Respectfully submitted,

Date: March 29, 2002



Jeffrey D. Myers, Reg. No. 35,964
Direct line: (505) 998-1502

Attorney for Applicant(s)
PEACOCK, MYERS & ADAMS, P.C
P.O. Box 26927
Albuquerque, New Mexico 87125-6927
Telephone: (505) 998-1500
Facsimile No. (505) 243-2542
Customer No. 005179

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)


JEFFREY D. MYERS, Reg. No. 35,964

Send Correspondence to: **CUSTOMER NO. 005179**




Direct Telephone Calls to: (name and telephone number)
Jeffrey D. Myers (505) 998-1500 direct line: (505) 998-1502

Full name of sole or first inventor LAURENTIUS CORNELIUS JOSEPHUS HESSELMANS	
Sole or first inventor's signature	Date
Residence 's-Hertogenbosch, the Netherlands	
Citizenship Dutch	
Post Office Address Vughterstraat 151b	
5211 GB 's-Hertogenbosch, the Netherlands	



Seen for legalization of the signature of: **P.C.J. Hesselman**
 residing at **DE BOSC**
 by me, civil-law notary Mr. F.J. van Lintel,
 on this day of **29-04-2002**

Full name of second inventor, if any DIRK PIETER SPEK	
Second inventor's signature	Date
Residence Meeuwen, the Netherlands	
Citizenship Dutch	
Post Office Address Hoog Meeuwen 19	
4268 GT Meeuwen, the Netherlands	



Seen for legalization of the signature of: **D.P. Spek**
 residing at **MEEUWEN**
 by me, civil-law notary Mr. F.J. van Lintel,
 on this day of **29-04-2002**

I hereby claim the benefit under 35 U.S.C. Section 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)

I hereby claim the benefit under 35 U. S. C. Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. Section 112, I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, C. F. R., Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.